

LEXAN™ RCX7243 resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

Lexan® RCX7243 is an impact modified PC blend containing 30% PCR content with non-brominated and non-chlorinated FR for thin-wall applications requiring excellent impact/flow balance performance.

General Information			
UL YellowCard	E207780-102079922		
Additive	Flame Retardant		
	Impact Modifier		
Recycled Content	Yes,30%		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Impact Modified		
Uses	Thin-walled Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	19	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.60	%	Internal Method
Water Absorption (Saturation, 23°C)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2400	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	58.0	MPa	
Break	53.0	MPa	
Tensile Elongation ³			ASTM D638
Yield	4.0	%	
Break	60	%	
Flexural Modulus ⁴ (50.0 mm Span)	2350	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
-30°C	130	J/m	ASTM D256
23°C	690	J/m	ASTM D256
23°C ⁶	50	kJ/m ²	ISO 180/1A

Instrumented Dart Impact (23°C, Total Energy)	57.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	101	°C	
1.8 MPa, Unannealed, 3.20 mm	86.0	°C	
Vicat Softening Temperature	104	°C	ASTM D1525 ⁷
CLTE			ASTM E831
Flow : -40 to 40°C	7.5E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.5E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.400 mm, Testing by SABIC	V-2		
0.600 mm, Testing by SABIC	V-1		
0.750 mm, Testing by SABIC	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	230 to 280	°C	
Middle Temperature	240 to 290	°C	
Front Temperature	250 to 300	°C	
Nozzle Temperature	250 to 300	°C	
Processing (Melt) Temp	250 to 300	°C	
Mold Temperature	60.0 to 85.0	°C	
Vent Depth	0.030 to 0.075	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		
6.	80*10*3		
7.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

