

POCAN® B 2505 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, flame retardant

General Information	
UL YellowCard	E245249-474013
Additive	Flame Retardant
Features	Flame Retardant
Processing Method	Injection Molding
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
	1.47		
Density (23°C)	1.47	g/cm ³	ISO 1183
Apparent Density	0.90	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 250°C, 2.00 mm ¹	2.2	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	%	
Flow : 250°C, 2.00 mm ³	2.2	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.20	%	
Water Absorption			ISO 62
	0.40		
Saturation, 23°C	0.40	%	
	0.20		
Equilibrium, 23°C, 50% RH	0.20	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	150	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method

Tensile Modulus			
23°C	2760	MPa	ASTM D638
23°C	3000	MPa	ISO 527-2/1
Tensile Stress			
Yield, 23°C	50.0	MPa	ISO 527-2/50
Break, 23°C	48.3	MPa	ASTM D638
Tensile Strain			
Yield, 23°C	3.0	%	ISO 527-2/50
Break, 23°C	16	%	ASTM D638
Nominal Tensile Strain at Break (23°C)	8.0	%	ISO 527-2/50
Tensile Creep Modulus			ISO 899-1
1 hr	2800	MPa	
1000 hr	1800	MPa	
Flexural Modulus			
23°C	2560	MPa	ASTM D790
23°C ⁵	3000	MPa	ISO 178/A
Flexural Strength			
23°C	85.5	MPa	ASTM D790
3.5% Strain, 23°C	80.0	MPa	ISO 178/A
23°C ⁶	90.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	5.0	%	ISO 178/A
Halving Interval			IEC 60216
Electric Strength	12.4	°C	
Tensile Impact Strength : 1.50 mm	9.2	°C	
Tensile Strength : 1.50 mm	11.7	°C	
Temperature Index			IEC 60216
Electric Strength, 20000 hr	145	°C	
Tensile Impact Strength, 20000 hr : 1.50 mm	135	°C	
Tensile Strength, 20000 hr : 1.50 mm	140	°C	
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GFMHR, 11-030; ISO 1043-PBT FR(17)		ISO 7792
	0.0 to 0.020		
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	90	kJ/m ²	

23°C	100	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	65	kJ/m ²	
23°C	80	kJ/m ²	
Multi-Axial Instrumented Impact Energy (23°C, Energy to Peak Force)		J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	170	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	°C	ISO 75-2/A
8.0 MPa, Unannealed	48.0	°C	ISO 75-2/C
Vicat Softening Temperature	190	°C	ISO 306/B120
Ball Pressure Test (190°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	1.0E-4	cm/cm/°C	
Transverse : 23 to 55°C	1.0E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp (1.50 mm)	130	°C	UL 746
RTI Str (1.50 mm)	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Electric Strength (23°C, 1.00 mm)	28	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.40		
23°C, 1 MHz	3.20		
Comparative Tracking Index (CTI)	600	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		
1.60 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Oxygen Index ⁹	32	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	

4.0 to 8.0

Drying Time - Circulation Dryer	4.0 to 8.0	hr
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	80.0 to 100	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min
9.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

