

TORZEN® G5000HS1L NC01

Polyamide 66

INVISTA Engineering Polymers

Message:

TORZEN® G5000HS1L NC01 is a 50% glass reinforced, heat stabilized, natural, PA66 resin suitable for many injection molding applications where high tensile strength and dimensional stability are needed.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Additive	heat stabilizer		
Features	Good dimensional stability		
	High tensile strength		
	Thermal Stability		
	Good demoulding performance		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	2.3	g/10 min	ASTM D1238
Molding Shrinkage			ISO 294-4
Transverse flow: 2.00mm	0.80 - 0.90	%	ISO 294-4
Flow: 2.00mm	0.20 - 0.30	%	ISO 294-4
Water Absorption			ISO 62
23°C, 24 hr	0.65	%	ISO 62
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16900	MPa	ISO 527-2
Tensile Stress (Break)	247	MPa	ISO 527-2
Tensile Strain (Break)	2.4	%	ISO 527-2
Flexural Modulus	16700	MPa	ISO 178
Flexural Stress	350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	14	kJ/m²	ISO 179
23°C	16	kJ/m²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
-30°C	100	kJ/m²	ISO 179

23°C	130	kJ/m ²	ISO 179
Notched Izod Impact (23°C)	13	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	260	°C	ISO 75-2/B
1.8 MPa, not annealed	255	°C	ISO 75-2/A
Melting Temperature	262	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.080 - 0.18	%	
Rear Temperature	250 - 270	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	270 - 290	°C	
Nozzle Temperature	270 - 290	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	50 - 90	°C	
Back Pressure	0.200 - 1.00	MPa	
Cushion	4.00 - 6.00	mm	
Vent Depth	7.0E-3 - 0.040	mm	
Screw Speed	Low rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT