

ULTEM™ 1110F resin

Polyether Imide

SABIC Innovative Plastics

Message:

Enhanced flow Polyetherimide (Tg 217C). ECO Conforming. US FDA and EU Food Contact compliant, NSF 51 listing. UL94 V0 and 5VA listing. Effective June 2007, this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HU1110.

General Information	
UL YellowCard	E121562-101048269
Features	ECO Compliant
	Food Contact Acceptable
	Good Flow
Agency Ratings	EU Eco
	EU Food Contact, Unspecified Rating
	FDA Food Contact, Unspecified Rating
	NSF 51
Processing Method	Injection Molding
Multi-Point Data	Instrumented Impact (Energy) (ASTM D3763)
	Instrumented Impact (Load) (ASTM D3763)
	Pressure-Volume-Temperature (PVT - Zoller Method)
	Tensile Fatigue
	Tensile Stress vs. Strain (ASTM D638)
	Thermal Conductivity vs. Temperature (ASTM E1530)
	Viscosity vs. Shear Rate (ASTM D3835)

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3720	MPa	ASTM D638
Tensile Strength ² (Yield)	110	MPa	ASTM D638
Tensile Elongation ³ (Break)	70	%	ASTM D638
Flexural Modulus ⁴ (100 mm Span)	3720	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 100 mm Span)	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Reverse Notch Izod Impact (3.20 mm)	1900	J/m	ASTM D256
Gardner Impact (23°C)	23.0	J	ASTM D3029

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	199	°C	ASTM D648
RTI Elec	170	°C	UL 746
RTI Imp	170	°C	UL 746
RTI Str	170	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ⁶	PLC 5		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 3		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2		UL 746
Hot-wire Ignition (HWI)	PLC 1		UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.750 mm	V-0		
3.00 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Nozzle Temperature	343 to 399	°C	
Processing (Melt) Temp	349 to 399	°C	
Mold Temperature	135 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	2.6 mm/min		
5.	2.6 mm/min		
6.	Tungsten Electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

