

DOMAMID® 6G30HCE

Polyamide 6

DOMO Engineering Plastics SPA

Message:

Polyamide 6, 30% glass fibre, for injection moulding.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2/1
Tensile Stress (Break)	180	MPa	ISO 527-2/5
Tensile Strain (Break)	3.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	14	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	218 to 222	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 95.0	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT