

Elastollan® 1185 A HFFR

Thermoplastic Polyurethane Elastomer (Polyether)

BASF Polyurethanes GmbH

Message:

Thermoplastic Polyether Polyurethane special products, halogen-free flame retardant.

Typical applications

Cable jackets, Films

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
Uses	Cable Jacketing		
	Film		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	86		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			DIN 53504
20% Strain	3.60	MPa	
100% Strain	6.00	MPa	
300% Strain	7.80	MPa	
Tensile Stress			DIN 53504
Yield ¹	12.0	MPa	
Yield	20.0	MPa	
Tensile Elongation			DIN 53504
Break ²	750	%	
Break	580	%	
Tear Strength ³	55	kN/m	ISO 34-1
Extrusion	Nominal Value	Unit	
Melt Temperature	175 to 220	°C	
NOTE			

1.	after storage in water at 80°C for 42 days
2.	after storage in water at 80°C for 42 days
3.	Method Bb, Angle (Nicked)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

