

Orgalloy® RS 6630

Polyamide 66 Alloy

Arkema

Message:

Orgalloy® RS 6630 is a Polyamide 66 Alloy (Nylon 66 Alloy) product filled with filler. It can be processed by extrusion, injection molding, profile extrusion, or resin transfer molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: heat resistant.

General Information				
Filler / Reinforcement	Filler			
Features	High Heat Resistance			
	Platable			
Forms	Pellets			
Processing Method	Extrusion			
	Injection Molding			
	Profile Extrusion			
	Resin Transfer Molding			
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1)			
	Viscosity vs. Shear Rate (ISO 11403-2)			
Physical	Dry	Conditioned	Unit	Test Method
Density	1270	1270	kg/m ³	ISO 1183 ¹
Melt volume-flow rate (275°C/2.16 kg)	8.00	--	cm ³ /10min	ISO 1133 ²
Water Absorption				ISO 62 ³
Saturation	1.9	--	%	
Equilibrium	0.70	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile modulus	--	8800	MPa	ISO 527-2 ⁴
Tensile Stress (Break)	--	140	MPa	ISO 527-2 ⁵
Tensile Strain (Break)	--	4.0	%	ISO 527-2 ⁶
Tensile Creep Modulus				ISO 899-1 ⁷
1 hr	--	7900	MPa	
1000 hr	--	5620	MPa	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2 ⁸
0.45 MPa	245	--	°C	
1.8 MPa	225	--	°C	

Vicat Softening Temperature (50°C/h, B (50N))	195	--	°C	ISO 306 ⁹
Melting Temperature ¹⁰	255	--	°C	ISO 11357-3 ¹¹
CLTE				ISO 11359-2 ¹²
Flow	1.8E-5	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface resistivity	--	> 1.0E+15	ohms	IEC 60093 ¹³
Volume resistivity	--	> 1.0E+13	ohms·m	IEC 60093 ¹⁴
Electric strength	34	34	kV/mm	IEC 60243-1 ¹⁵
Relative Permittivity				IEC 60250 ¹⁶
100 Hz	--	3.00		
1 MHz	--	4.00		
Dissipation Factor				IEC 60250 ¹⁷
100 Hz	--	0.029		
1 MHz	--	0.016		
Comparative tracking index	--	600		IEC 60112 ¹⁸
Flammability	Dry	Conditioned	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm)	HB	--		ISO 1210 ¹⁹
Burning Behav. at thickness h (3.20 mm)	HB	--		ISO 1210 ²⁰
NOTE				
1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
3.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
7.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			

9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
10.	10 °C/min
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
14.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
15.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
16.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
17.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
18.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
19.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
20.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

