

# Victron® 095C6

Polyetheretherketone

Asia International Enterprise (Hong Kong) Limited

## Message:

Polyaryletherketones (Abbr. PEEK) is a crystalline high performance polymer with outstanding heat resistance, excellent strength and thermal properties. PEEK can compete with metals in lots of fields, its uniquely structure and properties offer outstanding fatigue and abrasion resistances, self-lubricated, excellent electrical properties, radiation resistance, and can withstand extreme temperatures difference environments. PEEK are highly used in electronics and electrical, automotives, mechanical and chemical, aerospace, military, and many high-end industries.

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	Crystalline		
	Fatigue Resistant		
	Good Abrasion Resistance		
	Good Electrical Properties		
	High Heat Resistance		
	High Strength		
	Radiation (Gamma) Resistant		
Uses	Self Lubricating		
	Aerospace Applications		
	Automotive Applications		
	Electrical/Electronic Applications		
	Medical/Healthcare Applications		
Forms	Military Applications		
	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.20	%	
Flow	0.10	%	
Water Absorption (Saturation, 23°C)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	107		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	225	MPa	ISO 527-2/1270
Tensile Strain (Break)	2.0	%	ISO 527-2/50
Flexural Modulus <sup>1</sup>	18500	MPa	ISO 178
Flexural Stress <sup>2</sup>	330	MPa	ISO 178
Abrasion (23°C)	0.160		ISO 8295

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	8.0	kJ/m <sup>2</sup>	ISO 180
Unnotched Izod Impact Strength	30	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	320	°C	ISO 75-2/A
Vicat Softening Temperature	343	°C	ISO 306/B50
CLTE - Flow (-20 to 150°C)	1.0E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.90	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	< 1.0E+3	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT