

TOTAL Polypropylene PPH 7062

Polypropylene Homopolymer

TOTAL Refining & Chemicals

Message:

Polypropylene PPH 7062 is an antistatic homopolymer with a Melt Flow Index of 12 g/10 min.
Polypropylene PPH 7062 is intended for injection moulding applications of boxes, closures and household articles.

General Information			
Additive	Antistatic		
Features	Antistatic		
Uses	Closures		
	Household Goods		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm³	ISO 1183
Apparent Density	0.53	g/cm³	ISO 60
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1550	MPa	ISO 527-2
Tensile Stress (Yield)	32.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	1450	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m²	ISO 179
Notched Izod Impact Strength (23°C)	3.5	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	152	°C	ISO 306/A50
--	87.0	°C	ISO 306/B50
Melting Temperature (DSC)	165	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

