

TECHNIACE® TA-1500

Acrylonitrile Butadiene Styrene + Nylon

Nippon A&L; Inc.

Message:

TECHNIACE® TA-1500 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) material. It is available in Asia Pacific or North America for injection molding. Primary attribute of TECHNIACE® TA-1500: Heat Resistant.

General Information			
Features	Medium Heat Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.06	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (240°C/10.0 kg)	14.0	cm³/10min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	114		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	53.0	MPa	ISO 527-2
Flexural Modulus (23°C)	2050	MPa	ISO 178
Flexural Stress (23°C)	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	87.0	°C	ISO 75-2/A
CLTE - Flow (23 to 80°C)	6.5E-5	cm/cm/°C	JIS K7197
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	> 3.0	hr	
Rear Temperature	240 to 280	°C	
Middle Temperature	240 to 280	°C	
Front Temperature	240 to 280	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

