

Iupiace® EHM103R

Polyphenylene Ether + PS

Mitsubishi Engineering-Plastics Corp

Message:

Iupiace® EHM103R is a Polyphenylene Ether + PS (PPE+PS) material. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Iupiace® EHM103R: Antistatic.

General Information			
Additive	Antistatic		
Features	Antistatic		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow : 3.20 mm	0.85 to 1.1	%	
Flow : 3.20 mm	0.85 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2600	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	62.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	8.0	%	ISO 527-2
Flexural Modulus (23°C)	2700	MPa	ISO 178
Flexural Stress (23°C)	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	150	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+3	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	290 to 310	°C	
Middle Temperature	310 to 330	°C	
Front Temperature	310 to 330	°C	
Nozzle Temperature	310 to 330	°C	
Mold Temperature	110 to 130	°C	
Injection Pressure	20.0 to 150	MPa	
Injection Rate	Moderate		

Screw Speed

60 to 150

rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

