

ACRYLITE® Satinice df22 8N

Polymethyl Methacrylate Acrylic
Evonik Cyro LLC

Message:

ACRYLITE® Satinice df light diffusing acrylic polymers meet the demanding requirements for the injection molding or extrusion of lighting products in residential, industrial, office and automotive interior applications. These light diffusing acrylic polymers are available in four ACRYLITE® grades and an impact resistant grade.

Class
ASTM D-788-84 : 8
ASTM D-788-93 : PMMA0140V2

General Information	
Features	Good Weather Resistance
Uses	Automotive Applications
	Industrial Applications
	Lighting Applications
	Lighting Diffusers
Agency Ratings	EC 1907/2006 (REACH)
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Water Absorption (Equilibrium)	< 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3790	MPa	ASTM D638
Tensile Strength	79.3	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	4.0	%	
Break	4.0	%	
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Annealed)	105	°C	ASTM D648
Vicat Softening Temperature	119	°C	ASTM D1525
CLTE - Flow (0 to 100°C)	7.2E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.498		ASTM D542
Transmittance	88.0	%	ASTM D1003
Haze	94	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

