

Keplex® 3315GK

Polybutylene Terephthalate

Korea Engineering Plastics Co., Ltd

Message:

Keplex® 3315GK is a Polybutylene Terephthalate (PBT) material filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America.

Important attributes of Keplex® 3315GK are:

Flame Rated

Flame Retardant

Typical applications include:

Electrical/Electronic Applications

Automotive

General Information			
UL YellowCard	E120354-220474		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Features	Flame Retardant		
Uses	Automotive Applications		
	Connectors		
	Electrical Parts		
	Electrical/Electronic Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	103	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.5	%	ASTM D638
Flexural Modulus (23°C)	6370	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	167	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	44	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	200	°C	
Melting Temperature	222	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

