

Escorene™ Ultra UL 00728

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Message:

UL 00514 is a copolymer of ethylene and vinyl acetate. When the processing temperature is higher than 250 C (482 °F) in processing conditions, resin degradation may be caused.

General Information			
Physical	Nominal Value	Unit	Test Method
Vinyl Acetate Content	27.5	wt%	ExxonMobil Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	17.0	MPa	ASTM D638
Tensile Elongation ² (Break)	> 100	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	43.0	°C	ASTM D1525
Legal statement			
有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用			
NOTE			
1.	5.0 mm/min		
2.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

