

Ryton® R-4-240NA

Polyphenylene Sulfide

Solvay Specialty Polymers

Message:

Ryton® R-4-240NA and R-4-240BL 40% glass fiber reinforced polyphenylene sulfide compounds provide enhanced mechanical strength and toughness compared to other polyphenylene sulfide compounds.

General Information			
UL YellowCard	E95746-102108316		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Good Strength		
	Good Toughness		
Uses	Automotive Applications		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.66	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.50	%	
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	99		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	172	MPa	ASTM D638
--	185	MPa	ISO 527-2
Tensile Elongation			
Break	1.9	%	ASTM D638
Break	2.0	%	ISO 527-2
Flexural Modulus			
--	13800	MPa	ASTM D790
--	14000	MPa	ISO 178
Flexural Strength			
--	262	MPa	ASTM D790

--	275	MPa	ISO 178
Compressive Strength	265	MPa	ASTM D695
Poisson's Ratio	0.39		ISO 527
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
3.18 mm	91	J/m	ASTM D256
--	10	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	800	J/m	ASTM D4812
--	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648
CLTE			ASTM E831
Flow : -50 to 50°C	2.0E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	4.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	9.0E-5	cm/cm/°C	
Thermal Conductivity	0.31	W/m/K	
UL Temperature Rating	200 to 220	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.90		
25°C, 1 MHz	4.00		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	2.0E-3		
Arc Resistance	130	sec	ASTM D495
Comparative Tracking Index (CTI)	150	V	UL 746
Insulation Resistance ¹ (90°C)	1.0E+12	ohms	
Flammability	Nominal Value	Unit	Test Method
	V-0		
Flame Rating (1.60 mm)	5VA		UL 94
Oxygen Index	54	%	ASTM D2863
NOTE			
1.	95%RH, 48 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

