

Karina CLEAR PVC COMPOUND

60/207-DA-ATB

Polyvinyl Chloride
Karina Ind. e Com. de Plásticos Ltda

Message:
NON TOXIC PVC COMPOUND FREE OF PHTHALIC PLASTICIZERS RECOMMENDED FOR INJECTION MOLDING OF TOYS FOR CHILDREN WITH LESS THAN 3 YEARS OF AGE.

| General Information | | | |
|-------------------------------|-------------------|-------------------|-------------|
| Features | Non-Toxic | | |
| Uses | Toys | | |
| Appearance | Clear/Transparent | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity ¹ | 1.15 to 1.19 | g/cm ³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 58 to 62 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | > 5.88 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | > 200 | % | ASTM D638 |
| Abrasion Resistance | < 250 | mm ³ | DIN 53516 |
| Tear Resistance | > 15.0 | kN/m | DIN 53507 |
| Clearness | 0.00OK | | ME 03 |
| NOTE | | | |
| 1. | 24 hr | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT