# Marlex® 9503H

### High Density (HMW) Polyethylene

## Chevron Phillips Chemical Company LLC

#### Message:

Marlex® 9503H is a High Density (HMW) Polyethylene material. It is available in Latin America or North America for blow molding or extrusion. Important attributes of Marlex® 9503H are:

Antistatic

Eco-Friendly/Green
Food Contact Acceptable
Hexene Comonomer

High ESCR (Stress Crack Resistant)

Typical applications include:

Containers

**Bottles** 

Engineering/Industrial Parts

Food Contact Applications

General Information					
Additive	Antistatic				
Features	Antistatic				
	Durable				
	Food Contact Acceptable				
	Good Impact Resistance				
	Hexene Comonomer				
	High ESCR (Stress Crack Resist.)				
	High Molecular Weight				
	Recyclable Material				
Uses	Bottles				
	Containers				
	Industrial Containers				
	Industrial Parts				
Agency Ratings	ASTM D 4976-PE235				
	FDA 21 CFR 177.1520(c) 3.1a 2				
Forms	Pellets				
Processing Method	Blow Molding				
	Extrusion				
Physical	Nominal Value	Unit	Test Method		
Density	0.946	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	0.31	g/10 min	ASTM D1238		

Environmental Stress-Cracking Resistance				
(100% Igepal, Compression Molded, F50)	> 800	hr	ASTM D1693B	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength <sup>1</sup> (Yield, Compression				
Molded)	24.0	MPa	ASTM D638	
Tensile Elongation <sup>2</sup> (Break, Compression				
Molded)	500	%	ASTM D638	
Flexural Modulus - Tangent <sup>3</sup>				
(Compression Molded)	1030	MPa	ASTM D790	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	< -75.0	°C	ASTM D746A	
NOTE				
1.	Type IV, 51 mm/min			
2.	Type IV, 51 mm/min			
3.	13 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

