

Radilon® A V2 161 C NAT

Polyamide 66

Radici Plastics

Message:

PA66 flame retardant injection moulding grade. Natural colour.

Suitable for parts requiring UL-94 rating V2 at 0.8 mm. Typical application: household appliances.

ISO 1043 : PA66 FR(16+20)

General Information				
Additive	Flame Retardant			
Features	Flame Retardant			
Uses	Appliances			
	Household Goods			
RoHS Compliance	RoHS Compliant			
Appearance	Natural Color			
Processing Method	Injection Molding			
Resin ID (ISO 1043)	PA66 FR(16+20)			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.28	--	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3500	--	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	78.0	--	MPa	ISO 527-2/1A/50
Nominal Tensile Strain at Break	13	--	%	ISO 527-2/1A/50
Flexural Modulus ¹	3400	--	MPa	ISO 178
Flexural Stress ²	120	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	--	kJ/m ²	ISO 179/1eA
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	--	°C	ISO 75-2/Af
Vicat Softening Temperature	205	--	°C	ISO 306/B50
Melting Temperature ³	260	--	°C	ISO 11357
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms · cm	IEC 60093
Comparative Tracking Index	300	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Burning Rate	0.0	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	V-2	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
1.00 mm	850	--	°C	
2.00 mm	850	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
1.00 mm	800	--	°C	
2.00 mm	800	--	°C	
Injection	Dry	Unit		
Drying Temperature - Desiccant Dryer	80.0		°C	
Drying Time - Desiccant Dryer	2.0 to 4.0		hr	
Dew Point - Desiccant Dryer	< -20.0		°C	
Suggested Max Moisture	0.15		%	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	70.0 to 90.0		°C	
Injection Rate	Moderate			
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

