# THERMOLAST® K TF3THT (Series: FC/ht)

## Thermoplastic Elastomer

#### **KRAIBURG TPE**

#### Message:

The FC/ht Series is your highly transparent material solution for applications with food contact. The series is characterized, among other things, by its excellent adhesion to PP.

Typical applications

Function and design elements

**Grip applications** 

Household articles

Packaging (for food and careproducts)

Razors

Seals

Toothbrushes

Toys

Material advantages

Adhesion to PP

Code of Federal Regulations, Title 21 (CFR 21) "FDA"

EN71/3

Excellent processing behavior

**Excellent transparency** 

Regulation (EU) No. 10/2011

Smooth, non-tacky feel

Various color options and effects available (incl. transparent

colors, metallic & pearlescent effect)

od Contact Acceptable od Adhesion od Processability gh Clarity
od Processability
gh Clarity
od Packaging
usehold Goods
ckaging
als
othbrush Handles
ys
71-3
10/2011
A Food Contact, Unspecified Rating
ar/Transparent
lors Available
<i>+</i>

Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	30		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (Yield)	2.50	MPa	ISO 37
Tensile Elongation <sup>2</sup> (Break)	550	%	ISO 37
Tear Strength <sup>3</sup>	6.5	kN/m	ISO 34-1
Optical	Nominal Value	Unit	Test Method
Haze (2000 μm)	11	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	180	°C	
Middle Temperature	200	°C	
Front Temperature	220	°C	
Mold Temperature	50.0 to 60.0	°C	
Injection Pressure	20.0 to 100	MPa	
Back Pressure	2.00 to 10.0	MPa	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
3.	Method Bb, Angle (Nicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

