

CompaMid® PA 6.6 GF 15

Polyamide 66

DimeLika Plast GmbH

Message:

Our new crosslinkable CompaMid® PA 6.6 compounds are thermoplastic polymers which behave like elastomers over a wide temperature range as a result of beta radiation cross-linking. Thanks to crosslinking, the originally thermoplastic material can withstand significantly higher temperatures of up to 400°C, thus providing greater shape retention under thermal load. Due to its excellent performance profile, crosslinkable CompaMid® PA 6.6 can replace costly high-performance plastics such as PPA, PPS or LCP in many cases. No mould changes are required when switching from standard PA 6.6 to CompaMid® PA 6.6, and the process parameters also remain the same.

Electrical Applications

Thanks to their outstanding electrical and mechanical properties, crosslinkable CompaMid® PA 6.6 compounds are ideally suited for applications in the electrical and electronics industries.

Automotive Applications

Crosslinked components made of CompaMid® PA 6.6 are used in the engine bay and exhaust system, where requirements are the toughest for heat resistance and shape retention, as well as resistance to salts, chemicals and corrosive media.

| General Information | | | | |
|--------------------------------|-----------------------------------|-------------|--------------------|--------------|
| Filler / Reinforcement | Glass Fiber, 15% Filler by Weight | | | |
| Features | Crosslinkable | | | |
| | Good Electrical Properties | | | |
| Physical | Dry | Conditioned | Unit | Test Method |
| Density | 1.23 | -- | g/cm ³ | ISO 1183 |
| Molding Shrinkage ¹ | | | | ISO 294-4 |
| Across Flow : 80°C | 1.0 | -- | % | |
| Flow : 80°C | 0.60 | -- | % | |
| Water Absorption | | | | ISO 62 |
| Saturation, 23°C | 7.0 | -- | % | |
| Equilibrium, 23°C, 50% RH | 2.3 | -- | % | |
| Viscosity Number | 145 | -- | cm ³ /g | ISO 307 |
| Mechanical | Dry | Conditioned | Unit | Test Method |
| Tensile Modulus | 6100 | 4200 | MPa | ISO 527-2/1 |
| Tensile Stress | | | | ISO 527-2/50 |
| Yield | 140 | 80.0 | MPa | |
| Break | 130 | 85.0 | MPa | |
| Tensile Strain | | | | ISO 527-2/50 |
| Yield | 3.5 | 12 | % | |
| Break | 3.0 | 10 | % | |
| Impact | Dry | Conditioned | Unit | Test Method |
| Charpy Notched Impact Strength | | | | ISO 179/1eA |
| -30°C | 7.0 | 7.0 | kJ/m ² | |
| 23°C | 8.0 | 11 | kJ/m ² | |

| | | | | |
|---|-------------------|-------------|-------------------|-------------|
| Charpy Unnotched Impact Strength | | | | ISO 179/1eU |
| -30°C | 38 | 38 | kJ/m ² | |
| 23°C | 40 | 60 | kJ/m ² | |
| Thermal | Dry | Conditioned | Unit | Test Method |
| Heat Deflection Temperature | | | | |
| 0.45 MPa, Unannealed | 250 | -- | °C | ISO 75-2/B |
| 1.8 MPa, Unannealed | 235 | -- | °C | ISO 75-2/A |
| 8.0 MPa, Unannealed | 70.0 | -- | °C | ISO 75-2/C |
| Melting Temperature | 260 | -- | °C | ISO 11357-3 |
| CLTE | | | | ISO 11359-2 |
| Flow : 23 to 80°C | 3.4E-5 | -- | cm/cm/°C | |
| Transverse : 23 to 80°C | 7.0E-5 | -- | cm/cm/°C | |
| Heat Distortion | < 400 | < 400 | °C | |
| Electrical | Dry | Conditioned | Unit | Test Method |
| Surface Resistivity | 1.0E+10 | -- | ohms | IEC 60093 |
| Volume Resistivity | 1.0E+15 | -- | ohms·cm | IEC 60093 |
| Relative Permittivity (1 MHz) | 3.50 | -- | | IEC 60250 |
| Comparative Tracking Index (Solution A) | 550 | -- | V | IEC 60112 |
| Flammability | Dry | Conditioned | Unit | Test Method |
| Flame Rating (0.800 mm) | HB | -- | | UL 94 |
| NOTE | | | | |
| 1. | 260 °CWZ, 600 Bar | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT