

Andur 7501 DP

Polyurethane (Polyether, TDI)
Anderson Development Company

Message:

Andur 7501-DP is a polyether (PPG) based liquid, toluene diisocyanate terminated prepolymer. An elastomer with a hardness of 73 to 77 Shore D is obtained when this prepolymer is cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)]. Elastomers of lower hardness can be obtained by reaction with various polyols and their combination with Curene 442 and other diamines, or through the use of plasticizers.

General Information			
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity (100°C)	340	cP	ASTM D2393
Additional Information			

NCO: 7.3 to 7.7%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

