

TEPCON® M270

Acetal (POM) Copolymer
Polyplastics Co., Ltd.

Message:
Standard, High Fluidity, High Cycle

General Information			
UL YellowCard	E146187-223359		
Features	Copolymer		
	High Flow		
UL File Number	E146187		
Forms	Pellets		
Part Marking Code (ISO 11469)	>POM<		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	63.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	30	%	ISO 527-2
Flexural Modulus	2550	MPa	ISO 178
Flexural Stress	88.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.3	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
CLTE			Internal Method
Flow : 23 to 55°C	1.1E-4	cm/cm/°C	
Transverse : 23 to 55°C	1.1E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Electric Strength (3.00 mm)	19	kV/mm	IEC 60243-1
Comparative Tracking Index	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

