

Multilon® TN-7000

Polycarbonate + ABS

TEIJIN LIMITED

Message:

PC/ABS polymer alloy, Non-halogen type flame resistant series

General Information			
UL YellowCard	E98529-253693	E244324-101599329	
Features	Bromine Free		
	Flame Retardant		
Uses	Business Equipment		
	Office Automation Equipment		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	63.0	MPa	
Break	48.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	3.0	%	
Break	80	%	
Flexural Modulus ¹	2600	MPa	ISO 178
Flexural Stress ²	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	15	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	94.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	84.0	°C	ISO 75-2/A
Vicat Softening Temperature	97.0	°C	ISO 306/B50
CLTE			ISO 11359-2

Flow	8.0E-5	cm/cm/°C	
Transverse	8.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.700 mm	V-2		
1.20 mm	V-1		
1.50 mm	V-0		
2.00 mm	5VB		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

