

PPR ABS03

Acrylonitrile Butadiene Styrene
Premier Plastic Resins, Inc.

Message:

PPR ABS03 is an acrylonitrile butadiene styrene (ABS) product. It can be processed by injection molding and is available in North America.

General Information			
Features	Electroplateable		
Appearance	Grey		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	48.0	MPa	ASTM D638
Tensile Elongation (Break)	18	%	ASTM D638
Flexural Modulus - Tangent	2760	MPa	ASTM D790
Flexural Strength	76.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	103	°C	ASTM D648
1.8 MPa, not annealed	96.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	77.0 - 82.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	227 - 254	°C	
Middle Temperature	232 - 260	°C	
Front Temperature	232 - 260	°C	
Nozzle Temperature	243 - 254	°C	
Processing (Melt) Temp	227 - 260	°C	
Mold Temperature	49.0 - 77.0	°C	
Injection Pressure	5.00 - 55.0	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	3.00 - 45.0	MPa	
Back Pressure	0.00 - 1.00	MPa	
Cushion	6.35 - 12.7	mm	

Injection instructions

Screw Speed: Moderate-FastDecompression: 3.81 to 7.6 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

