

Borealis PE FS1560

High Density Polyethylene

Borealis AG

Message:

FS1560 is a high density polyethylene film grade which combine excellent extrusion behaviour with superior mechanical properties. Films made of FS1560 have high impact and tensile strength, and balanced tear properties. FS1560 contains antioxidant.

General Information			
Additive	Antioxidation		
Features	High tensile strength		
	Antioxidation		
	Impact resistance, high		
	Recyclable materials		
	Good tear strength		
Uses	Films		
	Lining		
	Bags		
	Heavy packing bag		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.956	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/21.6 kg	9.0	g/10 min	ISO 1133
190°C/5.0 kg	0.30	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Puncture Energy	1.50	J	ASTM D5748
Film Puncture Force	45.0	N	ASTM D5748
secant modulus			ASTM D882
MD	1000	MPa	ASTM D882
TD	1100	MPa	ASTM D882
Tensile Strength			ISO 527-3
MD	50.0	MPa	ISO 527-3
TD	55.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Fracture	250	%	ISO 527-3
TD: Fracture	300	%	ISO 527-3
Dart Drop Impact	350	g	ISO 7765-1

Elmendorf Tear Strength			ISO 6383-2
MD	0.20	N	ISO 6383-2
TD	0.30	N	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	127	°C	ISO 306
Melting Temperature	133	°C	ISO 11357-3
Extrusion	Nominal Value	Unit	
Melt Temperature	210 - 230	°C	
Extrusion instructions			

Blow Up Ratio: 3:1-5:1 Neck height: 5 - 9 X die diameter

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

