

Geon™ Vinyl Rigid Molding M5730

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Rigid Molding M5730 is a Rigid Polyvinyl Chloride product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Rigid Molding M5730 include construction applications and outdoor applications.

Characteristics include:

- Flame Rated
- High Flow
- Impact Resistant

General Information			
UL YellowCard	E41877-234299		
Features	General Purpose		
	High Flow		
	Medium Impact Resistance		
Uses	Construction Applications		
	General Purpose		
	Outdoor Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Spiral Flow	88.9	cm	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2340	MPa	ASTM D638
Tensile Strength ² (Yield)	42.7	MPa	ASTM D638
Tensile Elongation ³ (Break)	50	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	71.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
-18°C, 3.18 mm, Injection Molded	53	J/m	
0°C, 3.18 mm, Injection Molded	270	J/m	
23°C, 3.18 mm, Injection Molded	430	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	73.9	°C	

0.45 MPa, Annealed, 6.35 mm	77.8	°C	
1.8 MPa, Unannealed, 6.35 mm	72.2	°C	
1.8 MPa, Annealed, 6.35 mm	76.1	°C	
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm, ALL	V-0		
1.91 mm, ALL	5VA		
Injection	Nominal Value	Unit	
Processing (Melt) Temp	199 to 210	°C	
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		
3.	Type I, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

