

Premi-Glas® 2103-15 CR-SX

Thermoset, Unspecified

Premix, Inc.

Message:

Premi-Glas® 2103-15 CR-SX is a fiberglass reinforced thermoset bulk molding compound for electrical and flame retardant applications.

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Dimensional Stability		
	Good Stiffness		
	Good Thermal Stability		
	Halogen Free		
Uses	Electrical/Electronic Applications		
UL File Number	E42524		
Forms	BMC - Bulk Molding Compound		
Physical	Nominal Value	Unit	
Specific Gravity	1.70 to 1.85	g/cm ³	
Molding Shrinkage - Flow	0.15 to 0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12000	MPa	ASTM D638
Tensile Strength	31.0	MPa	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	95.0	MPa	ASTM D790
Poisson's Ratio	0.30		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	320	J/m	ASTM D256
Unnotched Izod Impact	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
CLTE			
Flow ¹	2.5E-5	cm/cm/°C	
Transverse ²	3.5E-5	cm/cm/°C	
Thermal Conductivity	0.30	W/m/K	
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	15	kV/mm	ASTM D149

Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index	600	V	ASTM D2303
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Mold Temperature	150	°C	
Injection Pressure	3.50 to 6.50	MPa	
NOTE			
1.	XY Direction		
2.	Z Direction		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT