

TAROMID A 280 H G6 DX0 TR1

Polyamide 66
Taro Plast S.p.A.

Message:

Polyamide 66 medium viscosity 30% glass fibres reinforced, flame retardant UL94 V0, heat stabilized, very good flame proofing also at low thickness. High mechanical and thermal properties, low shrinkage and high dimensional stability, high tracking resistance.

General Information			
UL YellowCard	E143048-223240		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
	Flame retardancy		
Features	Good dimensional stability		
	Track Resistance		
	Thermal Stability		
	Low shrinkage		
	Medium viscosity		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56 - 1.58	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Vertical flow direction	0.45 - 0.75	%	Internal method
Flow direction	0.30 - 0.50	%	Internal method
Water Absorption			ISO 62
23°C, 24 hr	0.50	%	ISO 62
Saturated, 23°C	4.5	%	ISO 62
Granule Humidity ¹		%	
Reaction to Fire	I2		NF F 16-101/102
Smoke Index	F3		NF F 16-101/102
Reinforcement Content ² (850°C)	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9400	MPa	ISO 527-2/1
Tensile Stress (Break)	145	MPa	ISO 527-2/50
Tensile Strain (Break)	2.2	%	ISO 527-2/50
Flexural Modulus ³	9200	MPa	ISO 178
Flexural Stress ⁴	206	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	32	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed)	240	°C	ISO 75-2/A
Vicat Softening Temperature	242	°C	ISO 306/B50
Ball Pressure Test (230°C)	Pass		IEC 60695-10-2
Melting Temperature	250 - 256	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Dielectric Strength (2.00 mm)	26	kV/mm	IEC 60243-1
Dielectric Constant	3.70		IEC 60250
Comparative Tracking Index (CTI)	PLC 1		UL 746
Comparative Tracking Index			IEC 60112
Solution a	> 400	V	IEC 60112
Solution B	> 250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	850	°C	IEC 60695-2-13
Oxygen Index	35	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	260 - 290	°C	
Mold Temperature	90.0 - 110	°C	
Injection Rate	Moderate		
Injection instructions			
Pre-heat Temperature: 80 to 100°CPre-heat Time: 3 hr			
NOTE			
1.	TARO 002		
2.	1 hr		
3.	1.0 mm/min		
4.	1.0 mm/min		
5.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

