

Manner Flexible PVC V962 NAT601/BLK 580

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Recommended Applications: General Purpose Tray Cable Jacket . This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Features	General Purpose		
Uses	Cable Jacketing		
	General Purpose		
	Wire & Cable Applications		
Appearance	Black		
	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36 to 1.40	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	82 to 88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	9.65	MPa	ASTM D638
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ¹ (121°C, 336 hr)	-3.0	%	UL 1581
Change in Ultimate Elongation in Air ² (121°C, 336 hr)	-4.0	%	UL 1581
Change in Tensile Strength (70°C, 4 hr, in IRM 902 Oil)	-3.0	%	
Change in Ultimate Elongation (70°C, 4 hr, in IRM 902 Oil)	5.0	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-25.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863
NOTE			
1.	Air Retention: .06 inch		
2.	Air Retention: .06 inch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT