

Staramide RF007ESS

Polyamide 66/6 Copolymer

Eurostar Engineering Plastics

Message:

Staramide RF007ESS a 35 % Glass Fiber Reinforced Polyamide 66 / Polyamide 6 Injection Molding Resin (also known as RF1007EMHS)

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.10 to 0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	178	MPa	ISO 527-2/5
Tensile Strain (Break)	2.4	%	ISO 527-2/5
Flexural Modulus ²	9100	MPa	ISO 178
Flexural Stress	235	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	50	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 64.0 mm Span)	237	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	270 to 290	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

