

SUPREME Specialty PS SP562

Ignition Resistant Polystyrene

Supreme Petrochem Ltd.

Message:

Flame Retardant Polystyrene (FR-HIPS)
Characteristics:
Ignition Resistant UL94 "V2" rated.
Very Good Flow Properties
Low Specific Gravity
Available in all colors
Free of DBDPO, PBDE & TBBA complies with RoHS directive of EU
Processing:
Molding
Applications:
Large size TV cabinets, Audio cabinets
Electrical boxes, Electrical appliance parts
Electrical distribution componenets, Fuse carriers, Enclosers

General Information			
Additive	Flame retardancy		
Features	Low density		
	Good liquidity		
	Flame retardant		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Home appliance components		
	Shell		
Agency Ratings	EU Unspecified Rating		
RoHS Compliance	RoHS compliance		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (23°C, 3.20 mm, Injection Molded)	29.0	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C, 3.20 mm, Injection Molded)	35	%	ASTM D638
Flexural Modulus (23°C, 3.20 mm, Injection Molded)	2100	MPa	ASTM D790

Flexural Strength (23°C, 3.20 mm, Injection Molded)	38.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm, Injection Molded)	81.0	°C	ASTM D648
Vicat Softening Temperature	97.0	°C	ASTM D1525 ³
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity (3.20 mm)	1.0E+14	ohms	IEC 60093
Volume Resistivity (3.20 mm)	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant (23°C, 3.20 mm, 1 MHz)	2.60		IEC 60250
Dissipation Factor (23°C, 3.20 mm, 1 MHz)	4.0E-4		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Additional Information			
Surface Resistivity, IEC 60093, 3.2mm: >1E14 ohmsVolume Resistivity, IEC 60093, 3.2mm: >1E16 ohm-cm			
Injection	Nominal Value	Unit	
Drying Temperature	60.0 - 80.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	250	°C	
Mold Temperature	40.0 - 60.0	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	标准 B (120°C/h), 压力1 (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

