

EVAL™ G156B

Ethylene Vinyl Alcohol

EVAL Europe nv

Message:

EVAL™ G156B is an Ethylene Vinyl Alcohol (EVOH) product. It is available in Europe.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	6.4	g/10 min	
210°C/2.16 kg	15	g/10 min	
Ethylene Content	48.0	mol%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Break)	22.0	MPa	ISO 527-2
Tensile Strain (Break)	14	%	ISO 527-2
Flexural Modulus	2800	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Oxygen Permeability ¹			ISO 14663-2
20°C, 0% RH	0.040	cm³ · mm/m²/atm/24 hr	
20°C, 100% RH	0.34	cm³ · mm/m²/atm/24 hr	
20°C, 35% RH	0.048	cm³ · mm/m²/atm/24 hr	
20°C, 65% RH	0.064	cm³ · mm/m²/atm/24 hr	
20°C, 85% RH	0.12	cm³ · mm/m²/atm/24 hr	
20°C, 90% RH	0.16	cm³ · mm/m²/atm/24 hr	
Water Vapor Transmission Rate ²	0.69	g · mm/m²/atm/24 hr	ASTM E96
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	1.8	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	50.0	°C	ISO 11357-2
Vicat Softening Temperature	146	°C	ISO 306
Melting Temperature	160	°C	ISO 11357-3
Peak Crystallization Temperature	138	°C	ISO 11357-3
NOTE			
1.	Annex C		
2.	Procedure E		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

