Hostacom TRC 160N

Polypropylene Copolymer LyondellBasell Industries

Message:

"Hostacom" TRC 160N is a 15% mineral filled, polypropylene copolymer for injection molding. It combines excellent stiffness/impact balance, good scratch resistance, low odor and excellent flowability properties with good dimensional stability. The grade has been specifically designed for molding of automotive interior trim parts. The grade is available in color-matched, pellet form.

| General Information | | | |
|------------------------------------|------------------------------|----------|-----------------|
| Filler / Reinforcement | Mineral,15% Filler by Weight | | |
| Features | Good Dimensional Stability | | |
| | Good Flow | | |
| | Good Stiffness | | |
| | Low to No Odor | | |
| | Scratch Resistant | | |
| Uses | Automotive Interior Parts | | |
| | Automotive Interior Trim | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.01 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2 | .16 | | |
| kg) | 14 | g/10 min | ISO 1133 |
| Molding Shrinkage | 0.90 to 1.1 | % | Internal Method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus - Secant | 1750 | MPa | ISO 527-2 |
| Tensile Stress (Yield) | 18.0 | МРа | ISO 527-2/50 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179/1eA |
| -30°C | 4.5 | kJ/m² | |
| 23°C | 45 | kJ/m² | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, Unannealed | 90.0 | °C | ISO 75-2/B |
| 1.8 MPa, Unannealed | 53.0 | °C | ISO 75-2/A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

