

VITAMIDE® AR38NT6513

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AR38NT6513 is a Polyamide 66 (Nylon 66) product filled with 40% glass fiber. It is available in Europe. Primary characteristic: heat stabilizer.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.0	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.00	MPa	ISO 527-2
Tensile Stress			
Yield	200	MPa	ISO 527-2
--	200	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638, ISO 527-2
Flexural Modulus	10500	MPa	ASTM D790, ISO 178
Flexural Stress			
--	290	MPa	ISO 178
Yield	290	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	12	kJ/m ²	ISO 179
Charpy Notched Impact Strength ¹	12.0	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength ²	75.0		ASTM D256
Charpy Unnotched Impact Strength	75	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	255	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	255	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	260	°C	ASTM D2117, ISO 1218
CLTE - Flow	2.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	35	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	450	V	IEC 60112

--	450	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863, ISO 4589-2
NOTE			
1.	Method B		
2.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT