

LNP™ THERMOCOMP™ UF00AAS compound

Polyphthalamide

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP UF00AAS is a compound based on Polyphthalamide resin containing Glass Fiber. Added features include: Heat Stabilized.

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.63	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.10 to 0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	234	MPa	ISO 527-2/5
Tensile Strain (Break)	1.6	%	ISO 527-2/5
Flexural Modulus ¹	14800	MPa	ISO 178
Flexural Stress	365	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	65	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	269	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	310 to 321	°C	
Middle Temperature	316 to 327	°C	
Front Temperature	327 to 338	°C	
Processing (Melt) Temp	316 to 332	°C	
Mold Temperature	138 to 166	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	2.0 mm/min		
2.	80*10*4		

3.	80*10*4
4.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

