

LEXAN™ 925AU resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN 925AU Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating and is UV stabilized, providing additional weathering capability. LEXAN 925AU resin is available in transparent and tinted color options and is a general-purpose resin that is an excellent candidate for a wide variety of applications.

General Information			
UL YellowCard	E121562-220902	E121562-499085	
Additive	Flame Retardant		
	UV Stabilizer		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	General Purpose		
Uses	General Purpose		
Appearance	Clear/Transparent		
	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 to 0.80	%	Internal Method
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2270	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	62.0	MPa	
Break	67.0	MPa	
Tensile Elongation ³			ASTM D638
Yield	6.0	%	
Break	130	%	
Flexural Modulus ⁴ (50.0 mm Span)	2370	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	800	J/m	ASTM D256

Instrumented Dart Impact (23°C, Total Energy)	79.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	137	°C	
1.8 MPa, Unannealed, 3.20 mm	126	°C	
Vicat Softening Temperature	143	°C	ASTM D1525 ⁶
CLTE			ASTM E831
Flow : -40 to 40°C	6.8E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.4E-5	cm/cm/°C	
RTI Elec	130	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Arc Resistance ⁷	PLC 7		ASTM D495
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 2		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-2		
3.04 mm	V-0		
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	280 to 310	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	280 to 310	°C	
Mold Temperature	80.0 to 110	°C	
NOTE			
1.	50 mm/min		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

6.	Rate B (120°C/h), Loading 2 (50 N)
7.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

