

SCHULAMID® RD 6 GF 30

Polyamide 6
A. Schulman Europe

Message:
30% glass fiber reinforced compound based on Polyamide 6

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Features		Good dimensional stability		
		Low density		
		Low hygroscopicity		
		Gloss, low		
		Noise reduction		
		Workability, good		
		Good liquidity		
		Hydrolysis resistance		
		Oil resistance		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA6-I-GF30		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.25	--	g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8700	6700	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	130	95.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	4.5	%	ISO 527-2/1A/5
Flexural Modulus	7000	--	MPa	ISO 178
Flexural Stress (3.3% strain)	180	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	--	kJ/m ²	ISO 179/1eA
23°C	15	17	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	46	--	kJ/m ²	ISO 179/1eU
23°C	56	60	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/Bf

1.8 MPa, not annealed	190	--	°C	ISO 75-2/Af
Vicat Softening Temperature				
--	220	--	°C	ISO 306/A50
--	175	--	°C	ISO 306/B50
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate	12	--	mm/min	ISO 3795
Flammability Classification				IEC 60695-11-10, -20
1.5 mm	HB	--		IEC 60695-11-10, -20
3.0 mm	HB	--		IEC 60695-11-10, -20
Additional Information				

干燥

1.)

Not for use in food contact applications2.)

Not for use in medical or pharmaceutical applicationsCharacteristic propertiesAs a semi-crystalline thermoplastic SCHULAMID® 6 possesses high rigidity,hardness and good cold impact resistance.

Injection	Dry	Unit	
Drying Temperature	80		°C
Drying Time	3.0 - 4.0		hr
Suggested Max Moisture	0.040 - 0.10		%
Suggested Max Regrind	20		%
Processing (Melt) Temp	250 - 280		°C
Mold Temperature	60 - 100		°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

