

Kingfa PET-RG15

Polyethylene Terephthalate

Kingfa

Message:

Kingfa PET-RG15 is a polyethylene terephthalate (PET) material, which contains a 15% glass fiber reinforced material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main features of Kingfa PET-RG15 are:

- flame retardant/rated flame
- Flame Retardant
- high strength
- Heat resistance

The typical application areas of Kingfa PET-RG15 are: electrical/electronic applications

General Information			
UL YellowCard	E171666-225753		
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	High strength		
	Good electrical performance		
	Heat resistance, medium		
	Flame retardancy		
Uses	Connector		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 23°C	0.50	%	ASTM D955
Transverse flow: 23°C	1.1	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	105	MPa	ASTM D638
Tensile Elongation ² (Break)	2.6	%	ASTM D638
Flexural Modulus ³	7000	MPa	ASTM D790
Flexural Strength ⁴	170	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	70	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	230	°C	ASTM D648

1.8 MPa, unannealed, 6.40mm	215	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 5.0	hr	
Rear Temperature	235 - 255	°C	
Middle Temperature	245 - 265	°C	
Front Temperature	255 - 275	°C	
Processing (Melt) Temp	255 - 275	°C	
Mold Temperature	80.0 - 120	°C	
Injection Rate	Moderate-Fast		
Injection instructions			
Processing Temperature Limit: 270°C			
NOTE			
1.	10 mm/min		
2.	10 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

