

VITAMIDE® BK30OR6540

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BK30OR6540 is a Polyamide 6 (Nylon 6) product. It is available in Europe. Primary characteristic: flame rated.

General Information			
Appearance	Orange		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	2.6	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	73.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	300	%	ASTM D638, ISO 527-2
Flexural Modulus	2200	MPa	ASTM D790, ISO 178
Flexural Stress			
--	83.0	MPa	ISO 178
Break	83.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	193	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	218	°C	ASTM D2117, ISO 1218
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+13	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	35	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

