

TECHNO AES W200

Acrylonitrile Ethylene Styrene

Techno Polymer Co, Ltd.

Message:

TECHNO AES W200 is an Acrylonitrile Ethylene Styrene (AES) product. It can be processed by injection molding and is available in Asia Pacific or North America.

Characteristics include:

- Flame Rated
- Good Weather Resistance
- High Flow
- Rigid

General Information			
UL YellowCard	E54297-244105		
Features	Good Weather Resistance		
	High Flow		
	Medium Rigidity		
UL File Number	E54297		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	47	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	111		ASTM D785
R-Scale	110		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	53.9	MPa	ASTM D638
Yield	51.0	MPa	ISO 527-2
Flexural Modulus			
--	2750	MPa	ASTM D790
--	2500	MPa	ISO 178
Flexural Strength			
--	90.2	MPa	ASTM D790
--	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Notched Izod Impact	78	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	92.0	°C	ASTM D648
0.45 MPa, Unannealed	78.0	°C	ISO 75-2/B
Flammability	Nominal Value		Test Method
Flame Rating (ALL)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	2.0 to 5.0	hr	
Rear Temperature	190 to 260	°C	
Middle Temperature	190 to 260	°C	
Front Temperature	190 to 260	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

