

Moplen F20S

Polypropylene Homopolymer
Shazand (Arak) Petrochemical Corporation

Message:

Moplen F20S is a polypropylene homo-polymer designed for the production of medium-low denier staple fibres.
Moplen F20S is a medium gas fading resistance and it is suitable for BCF and CFmultifilament, medium-low denier staple yarn and triobe sections.
* Moplen F20S is suitable for food contact.

General Information			
Features	Food Contact Acceptable		
	Gas-fading Resistant		
	Homopolymer		
Uses	BCF Yarn		
	Fibers		
	Filaments		
	Staple Fibers		
	Yarn		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	37.0	MPa	ASTM D638
Tensile Elongation (Yield)	11	%	ASTM D638
Flexural Modulus	1600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256
Aging	Nominal Value	Unit	Test Method
Oven Aging (150°C)	10.4	day	ASTM D3012
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	97.0	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 ¹
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

