

Network Polymers SAN 279

Styrene Acrylonitrile

Network Polymers, Inc.

Message:

Network Polymers SAN 279 is a Styrene Acrylonitrile (SAN) product. It can be processed by injection molding and is available in North America. Typical application: Food Contact Applications. Primary characteristic: flame rated.

General Information			
Agency Ratings	FDA 21 CFR 181.32(a)(3)(ii)		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 kg	2.0	g/10 min	
230°C/3.8 kg	7.5	g/10 min	
Molding Shrinkage - Flow	0.30 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	71.7	MPa	ASTM D638
Flexural Modulus - Tangent ³	3450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	88.9	°C	ASTM D648
Vicat Softening Temperature	101	°C	ASTM D1525 ⁴
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance	89.0	%	ASTM D1003
Haze	1.9	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Shot Size	40 to 75	%	
Rear Temperature	160 to 182	°C	
Middle Temperature	182 to 221	°C	
Front Temperature	193 to 232	°C	
Nozzle Temperature	193 to 232	°C	

Processing (Melt) Temp	193 to 216	°C
Mold Temperature	26.7 to 76.7	°C
Injection Pressure	0.414 to 7.58	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.517 to 1.03	MPa
Clamp Tonnage	2.8 to 4.1	kN/cm ²

NOTE

- | | |
|----|------------------|
| 1. | Procedure A |
| 2. | 51 mm/min |
| 3. | 1.3 mm/min |
| 4. | Loading 1 (10 N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT