

Durethan® AKV 25 FN 00 000000

Polyamide 66

LANXESS GmbH

Message:

PA 66, 25 % glass, injection molding, halogen free flame retardant

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 25% filler by weight		
Additive		Flame retardancy		
Features		Halogen-free		
		Flame retardancy		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA GF FR (30+40)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.39	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (270°C/2.16 kg)	12.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				ISO 2577
Vertical flow direction: 270°C, 2.00mm ¹	0.90	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.10	--	%	ISO 2577
Flow direction: 270°C, 2.00mm ³	0.30	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	4.6	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9600	5800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	125	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	6.0	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	3.4	--	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	9100	5700	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	--	120	MPa	ISO 178/A

23°C ⁶	210	135	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.3	5.8	%	ISO 178/A
ISO Shortname	PA 66, GFHR, 14-100, GF25	--		ISO 1874
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	< 10	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	60	kJ/m ²	ISO 179/1eU
23°C	60	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	55	65	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	225	--	°C	ISO 75-2/A
Vicat Softening Temperature	225	--	°C	ISO 306/B120
Ball Pressure Test (228°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁸	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.1E+16	--	ohms	IEC 60167
Volume Resistivity (23°C)	7.4E+15	--	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.400 mm	V-0	--		UL 94
0.750 mm	V-0	--		UL 94
1.50 mm	V-0	--		UL 94
3.00 mm	V-0	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.400 mm	960	--	°C	IEC 60695-2-12
0.800 mm	960	--	°C	IEC 60695-2-12
1.50 mm	960	--	°C	IEC 60695-2-12
3.00 mm	960	--	°C	IEC 60695-2-12

Glow Wire Ignition Temperature				IEC 60695-2-13
0.400 mm	775	--	°C	IEC 60695-2-13
0.750 mm	775	--	°C	IEC 60695-2-13
1.50 mm	775	--	°C	IEC 60695-2-13
3.00 mm	775	--	°C	IEC 60695-2-13
Oxygen Index ⁹	38	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	265 - 285		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				

1.	60x60x2mm, 120°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 120°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min
9.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

