

Tribocomp® PA66 LGF30 TS0 S8

Polyamide 66
Solvay Specialty Polymers

Message:

Tribocomp® PA66 LGF30 TS0 S8, is a 30% long glass fiber reinforced black high-flow PA 66 with a pellet length of 8mm and contains 15% PTFE having excellent tribological performance. It can easily be processed on most injection molding machines.

General Information				
Filler / Reinforcement		PTFE fiber, 15% filler by weight Long glass fiber, 30% filler by weight		
Appearance		Black		
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.50	--	g/cm ³	ISO 1183
shrinkage-Flow	0.40	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.4	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
23°C	10500	7900	MPa	ISO 527-2
90°C	7100	--	MPa	ISO 527-2
120°C	5500	--	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Fracture, 23°C	190	150	MPa	ISO 527-2
Fracture, 90°C	120	--	MPa	ISO 527-2
Fracture, 120°C	95.0	--	MPa	ISO 527-2
Tensile Strain (Break)	3.0	--	%	ISO 527-2
Flexural Modulus (23°C)	8300	6200	MPa	ISO 178
Flexural Stress (23°C)	260	200	MPa	ISO 178
Coefficient of Friction				ASTM D3702
Dynamic	0.23	--		ASTM D3702
Static	0.18	--		ASTM D3702
Wear Factor	13.0	--		ASTM D3702
Coefficient of Linear Thermal Expansion	2.9E-5	--	cm/cm/°C	ISO 11359-2
Surface Resistivity	1.0E+13	--	ohms/sq	ASTM D257
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	19	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	65	--	kJ/m ²	ISO 179

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	255	--	°C	ISO 75-2/B
1.8 MPa, not annealed	253	--	°C	ISO 75-2/A
Thermal Conductivity	0.29	--	W/m/K	ISO 22007
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength (2.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	500	--	V	IEC 60112
Additional Information				

干燥

The value listed as Molding Shrinkage ISO 294-4, was tested in accordance with S.O.P. methods.

Injection	Dry	Unit
Drying Temperature	100	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	270 - 300	°C
Middle Temperature	270 - 300	°C
Front Temperature	285 - 300	°C
Nozzle Temperature	285 - 310	°C
Processing (Melt) Temp	< 300	°C
Mold Temperature	80 - 140	°C

Injection instructions

Pre-drying -- Since polyamides are hygroscopic materials as well as sensitive to moisture during processing, this product should always be pre-dried. Regrind -- Regrind of highly filled thermoplastic materials, such as this material, should only be recycled with special care. The regrind content must never exceed 15%, and only regrind of optimum quality should be used. In any case, part properties should be checked.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT