

Rotec® ABS 1001 FRVO

Acrylonitrile Butadiene Styrene

ROMIRA GmbH

Message:

Rotec® ABS 1001 FRVO is an acrylonitrile butadiene styrene (ABS) material. This product is available in Europe. Rotec® The main characteristics of ABS 1001 FRVO are: flame retardant/rated flame.

General Information			
UL File Number	148878		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	70	g/10 min	ISO 1133
Molding Shrinkage	0.60	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	60.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2
Flexural Modulus (23°C)	2200	MPa	ISO 178
Flexural Stress (23°C)	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
	6.0		
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	95.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Additional Information			

Most tests were performed under DIN test standards. Density, DIN 53479, 23°C, 50% RH: 1.18 g/ml Charpy Notched Bar Impact Strength, ISO 179, 23°C, Type 1, Edgewise, Notch A, 80x10x4, Natural: 7 kJ/m² Charpy Notched Bar Impact Strength, ISO 179, 23°C, Type 1, Edgewise, Notch A, 80x10x4, Color: 6 kJ/m² Charpy Unnotched Impact Strength, ISO 179, 23°C, Type 1, Edgewise, 80x10x4, Color/Natural: 60 kJ/m²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

