

ALTECH® PA6 A 2015/310 GF15 IM

BK0004-00LS

Polyamide 6

ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 A 2015/310 GF15 IM BK0004-00LS is a Polyamide 6 (Nylon 6) product filled with 15% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALTECH® PA6 A 2015/310 GF15 IM BK0004-00LS include electrical/electronic applications, engineering/industrial parts, housings and tools.

Characteristics include:

- REACH Compliant
- RoHS Compliant
- Heat Stabilizer
- Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Heat Stabilized		
	Impact Modified		
	Laser Markable		
Uses	Electrical/Electronic Applications		
	Housings		
	Machine/Mechanical Parts		
	Power/Other Tools		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4600	MPa	ISO 527-2
Tensile Stress			ISO 527-2
	Break	84.0	MPa
--	90.0	MPa	
Tensile Strain (Break)	4.5	%	ISO 527-2
Flexural Modulus	3800	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	65	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	190	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Desiccant Dryer	60.0 to 80.0	°C	
Drying Time - Desiccant Dryer	2.0 to 6.0	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	80.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

