

VALOX™ ENH8530 resin

Polybutylene Terephthalate + PET

SABIC Innovative Plastics Europe

Message:

Non-Brominated & Non-Chlorinated Flame Retardant, 15% Glass fiber reinforced PBT/PET blend

General Information			
UL YellowCard	E45329-100700420		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
265°C/2.16 kg	20	g/10 min	ASTM D1238
250°C/5.0 kg	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR)			
250°C/5.0 kg	11.0	cm ³ /10min	ASTM D1238
265°C/1.2 kg	5.00	cm ³ /10min	ISO 1133
265°C/2.16 kg	13.0	cm ³ /10min	ISO 1133
265°C/5.0 kg	45.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Ball Indentation Hardness (H 358/30)	142	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7200	MPa	ASTM D638
--	7400	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	75.0	MPa	ASTM D638
Yield	75.0	MPa	ISO 527-2/5
Break ³	75.0	MPa	ASTM D638
Break	75.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	2.0	%	ISO 527-2/5

Break ⁵	2.0	%	ASTM D638
Break	2.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	6000	MPa	ASTM D790
-- ⁷	6300	MPa	ISO 178
Flexural Stress			
--	125	MPa	ISO 178
Yield, 50.0 mm Span ⁸	110	MPa	ASTM D790
Break, 50.0 mm Span ⁹	110	MPa	ASTM D790
Flexural Strain at Break ¹⁰	3.0	%	ISO 178
Filler Content	15	%	ASTM D229
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/2C
-30°C	5.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/2U
-30°C	20	kJ/m ²	
23°C	23	kJ/m ²	
Notched Izod Impact			
-30°C	45	J/m	ASTM D256
0°C	45	J/m	ASTM D256
23°C	45	J/m	ASTM D256
-30°C ¹¹	5.0	kJ/m ²	ISO 180/1A
0°C ¹²	5.0	kJ/m ²	ISO 180/1A
23°C ¹³	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	280	J/m	ASTM D4812
23°C	330	J/m	ASTM D4812
-30°C ¹⁴	20	kJ/m ²	ISO 180/1U
23°C ¹⁵	22	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	215	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁶	215	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	190	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁷	180	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	220	°C	ASTM D1525 ¹⁸
--	202	°C	ASTM D1525 ¹⁹
--	215	°C	ISO 306/A50
--	196	°C	ISO 306/B50
--	200	°C	ISO 306/B120

Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			ISO 11359-2
Flow : -40 to 40°C	3.1E-5	cm/cm/°C	
Flow : 23 to 150°C	4.6E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.3E-5	cm/cm/°C	
Transverse : 23 to 150°C	1.7E-4	cm/cm/°C	
RTI Elec	75.0	°C	UL 746
RTI Imp	75.0	°C	UL 746
RTI Str	75.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength			ASTM D149, IEC 60243-1
0.800 mm, in Oil	38	kV/mm	
1.60 mm, in Oil	28	kV/mm	
3.20 mm, in Oil	19	kV/mm	
Dielectric Constant (1 MHz)	3.30		ASTM D150, IEC 60250
Dissipation Factor (1 MHz)	0.010		ASTM D150, IEC 60250
Comparative Tracking Index (CTI)	PLC 1		UL 746
Comparative Tracking Index	400	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
1.50 mm, Testing by SABIC	V-0		
2.00 mm	5VA		
Glow Wire Flammability Index (3.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (3.00 mm)	800	°C	IEC 60695-2-13
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C, 1500 sec ⁻¹)	145	Pa·s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	40.0 to 60.0	°C	
Rear Temperature	240 to 260	°C	
Middle Temperature	255 to 280	°C	
Front Temperature	260 to 280	°C	
Nozzle Temperature	265 to 275	°C	
Processing (Melt) Temp	260 to 285	°C	
Mold Temperature	60.0 to 110	°C	

NOTE	
1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	1.3 mm/min
10.	2 mm/min
11.	80*10*4
12.	80*10*4
13.	80*10*4
14.	80*10*4
15.	80*10*4
16.	80*10*4 mm
17.	80*10*4 mm
18.	Rate A (50°C/h), Loading 2 (50 N)
19.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

