

Tecopet® PT74 GR30 BK002 XA20

Polyethylene Terephthalate
Eurotec Engineering Plastics

Message:

PET, 30% glass fiber reinforced, flame retardant - halogen (RoHS compliant), heat stabilized, black

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
	Heat Stabilizer		
Features	Flame Retardant		
	Heat Stabilized		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PET GF30 FR(17)		
Physical	Nominal Value	Unit	Test Method
Density	1.69	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.90	%	
Flow	0.20	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 0.080	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	10500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	130	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	7.0	kJ/m ²	
23°C	8.0	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	35	kJ/m ²	
23°C	40	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
Melting Temperature ¹	250	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120 to 140	°C	
Drying Time	4.0	hr	
Hopper Temperature	50.0 to 70.0	°C	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	120 to 140	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	60.0 to 100	MPa	
NOTE			
1.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

