

Latamid 66 H2 K/50

Polyamide 66

LATI S.p.A.

Message:

Compound based on Polyamide 66 (PA 66). Heat stabilised. Carbon fibre.

General Information			
Filler / Reinforcement	Carbon Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.35 to 0.55	%	
Flow : 2.00 mm	0.10 to 0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	29000	MPa	
60°C	27000	MPa	
90°C	17500	MPa	
120°C	12000	MPa	
150°C	9500	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	210	MPa	
Break, 60°C	170	MPa	
Break, 90°C	140	MPa	
Break, 120°C	125	MPa	
Break, 150°C	100	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	1.0	%	
Break, 60°C	1.5	%	
Break, 90°C	2.4	%	
Break, 120°C	2.8	%	
Break, 150°C	2.9	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	70	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	°C	ISO 75-2/A
Continuous Use Temperature ²	135	°C	
Vicat Softening Temperature	255	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	2.0E-6	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10	ohms	ASTM D257
Volume Resistivity	50	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	280 to 310	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

