

PP ABS HF380

Acrylonitrile Butadiene Styrene
Performance Plastics, Ltd.

Message:
HF380 ABS: General Purpose High Flow Grade

General Information			
Features		General Purpose High Flow	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	4.0	g/10 min	
220°C/10.0 kg	43	g/10 min	
230°C/3.8 kg	15	g/10 min	
Molding Shrinkage - Flow	0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	44.4	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	> 5.0	%	
Break	> 10	%	
Flexural Modulus ³	2420	MPa	ASTM D790
Flexural Strength ⁴	71.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact			ASTM D256
-30°C, 3.20 mm	120	J/m	
-30°C, 6.40 mm	120	J/m	
23°C, 3.20 mm	260	J/m	
23°C, 6.40 mm	250	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	89.0	°C	
0.45 MPa, Annealed, 6.40 mm	91.0	°C	
1.8 MPa, Unannealed, 6.40 mm	86.0	°C	
1.8 MPa, Annealed, 6.40 mm	90.0	°C	
Vicat Softening Temperature	94.0	°C	ASTM D1525 ⁵
Electrical	Nominal Value	Unit	Test Method

Arc Resistance	PLC 6	ASTM D495	
Comparative Tracking Index (CTI)	PLC 1	UL 746	
High Amp Arc Ignition (HAI)	PLC 0	UL 746	
High Voltage Arc Tracking Rate (HVTR)	PLC 1	UL 746	
Hot-wire Ignition (HWI)	PLC 3	UL 746	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Flammability (3.20 mm)	FH3-35	mm/min	IEC 707
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	15 mm/min		
4.	15 mm/min		
5.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

